

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.01193	100.0	0.25513
			Subtotal	0.01193	100	0.25513
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.24327	90.0	5.202
	Tin alloy	Nickel (Ni) - cas no. 7440-02-0	7440-02-0	0.00135	0.5	0.0289
	Tin alloy	Silver (Ag)	7440-22-4	0.00676	2.5	0.1445
	Tin alloy	Antimony (Sb)	7440-36-0	0.01892	7.0	0.4046
			Subtotal	0.2703	100	5.78
Die	Doped silicon	Silicon (Si)	7440-21-3	0.29462	100.0	6.3
			Subtotal	0.29462	100	6.3
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.18708	100.0	4.00047
			Subtotal	0.18708	100	4.00047
Heat Spreader	Copper alloy	Phosphorous (P)	7723-14-0	0.01684	0.03	0.36
	Copper alloy	Iron (Fe)	7439-89-6	0.05612	0.1	1.2
	Copper alloy	Copper (Cu)	7440-50-8	56.04546	99.87	1,198.44
			Subtotal	56.11842	100	NaN
Post-plating	Pure Metal	Tin (Sn)	7440-31-5	1.26266	100.0	27
			Subtotal	1.26266	100	27
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00561	0.03	0.12
	Copper alloy	Iron (Fe)	7439-89-6	0.01871	0.1	0.4
	Copper alloy	Copper (Cu)	7440-50-8	18.68182	99.87	399.48
			Subtotal	18.70614	100	400
Die Attach	Lead alloy	Tin (Sn)	7440-31-5	0.05846	5.0	1.25
	Lead alloy	Silver (Ag)	7440-22-4	0.02923	2.5	0.625
	Lead alloy	Lead (Pb)	7439-92-1	1.08145	92.5	23.125
			Subtotal	1.16914	100	25
Isolator	Copper alloy	Phosphorous (P)	7723-14-0	0.00421	0.1	0.09
	Copper alloy	Aluminium Trioxide (Al2O3)	1344-28-1	3.85533	91.6	82.44
	Copper alloy	Nickel (Ni) - cas no. 7440-02-0	7440-02-0	0.03788	0.9	0.81
	Copper alloy	Molybdenum (Mo)	7439-98-7	0.29462	7.0	6.3
	Copper alloy	Manganese (Mn)	7439-96-5	0.01684	0.4	0.36
			Subtotal	4.20888	100	90
Mould Compound	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	0.26656	1.5	5.7
	Polymer	Epichlorohydrin/Diethyleneglycol Epoxy resin (generic)	25928-94-3	1.68823	9.5	36.1
	Filler	Silica fused	60676-86-0	15.63833	88.0	334.4
	Carbon Black	Carbon black	1333-86-4	0.17771	1.0	3.8
			Subtotal	17.77083	100	380
			Total	100	100	NaN

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.