

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.01284	100.0	0.26839
			Subtotal	0.01284	100	0.26839
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.0151	10.0	0.31549
	Silver alloy	Silver (Ag)	7440-22-4	0.00302	2.0	0.0631
	Lead alloy	Lead (Pb)	7439-92-1	0.13284	88.0	2.77629
			Subtotal	0.15096	100	3.15488
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.10068	100.0	2.10415
			Subtotal	0.10068	100	2.10415
Die	Doped silicon	Silicon (Si)	7440-21-3	0.16269	100.0	3.4
			Subtotal	0.16269	100	3.4
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00703	0.03	0.14694
	Pure metal layer	Zinc (Zn)	7440-66-6	0.00469	0.02	0.09796
	Pure metal layer	Tin (Sn)	7440-31-5	0.00703	0.03	0.14694
	Pure metal layer	Iron (Fe)	7439-89-6	0.02578	0.11	0.53877
	Pure metal layer	Copper (Cu)	7440-50-8	23.3917	99.81	488.8594
			Subtotal	23.43623	100	489.79001
Post-plating	Pure metal	Tin (Sn)	7440-31-5	0.24724	100.0	5.167
			Subtotal	0.24724	100	5.167
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	2.27668	3.0	47.58
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.55336	6.0	95.16
	Polymer	Epichlorohydrin/o-Cresol/Formaldehyde polymer (generic)	29690-82-2	7.58894	10.0	158.6
	Carbon Black	Carbon black	1333-86-4	0.37945	0.5	7.93
	Filler	Misc. Silica compounds (generic)	14808-60-7	59.1937	78.0	1237.08
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	1.89723	2.5	39.65
			Subtotal	75.88936	100	1586
			Total	100	100	2089.88443

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.